

Immersion Heaters Solvent

CHEMISTRY	STEEL	304 STAINLESS	316 STAINLESS	TITANIUM	ZIRCONIUM	FLUOROPOLYMER	QUARTZ	BATH EFFICIENCY	SPECIFIC HEAT	DENSITY	MAXIMUM WATT DENSITY
Amyl Acetate	-	✓	✓	✓	✓	✓	✓	-	-	-	
Aniline	-	✓	✓	✓	✓	✓	✓	-	0.51	8.53	
Naptha	-	✓	✓	✓	✓	✓	-	-	-	-	40
Trichloroethylene	-	-	✓	-	-	-	-	-	0.23	12.27	20